WAKOL D 3110 Modular Flooring Fixation

Technical Information

Area of application

Fixer dispersion for the laying of

- modular textile floor coverings
- self-laying LVT flooring
- CV Flooring

without multiple restarts on properly prepared absorbent and non-absorbent subfloors indoors.

Special Features

1) 2) 3) 4) 5) 6)

- solvent-free as defined by TRGS 610
- can be exposed directly to stresses and loads
- no residual impressions from compressed adhesive
- long open time
- electrical conductivity can be achieved when used in combination with WAKOL DL 352 Conductive Dispersion

1) Based on the criteria of GEV (Association for Emission-controlled Laying Materials), classified as EMICODE EC1 PLUS: very low in emissions
2) Emissions class according to French law
3) Solvent-free dispersion laying materials
4) Emissions-certified construction product i.a.w. ABG principles: Wakol GmbH, 66954 Pirmasens
5) Suitable for underfloor heating
6) Suitable for exposure to castor wheels

Technical data

Raw material base:	Polymer dispersion
Airing time:	approx. 20 minutes on absorbent subfloors, approx. 35 minutes on non-absorbent subfloors
Open time:	approx. 24 hours
Cleaning agent:	Water

Storage temperature:	not below +5 °C, sensitive to frost
Storage time:	12 months at room temperature

Application and consumption[7)]

Short-haired velour roller	80 - 120 g/m²	modular textile tiles self-laying LVT flooring Cushioned vinyl flooring

7) Consumption is dependent on surface structure and absorbability of subfloor.

Subfloors

The subfloor as well as the room climate conditions must meet the requirements of the applicable standards and data sheets. Subfloors must be permanently dry, solid, level, free from cracks, dirt and adhesion-inhibiting substances.

Smooth uneven subfloors with corresponding levelling compounds. We recommend the knife technique for achieving a smooth surface.

Usage

Stir the fixing agent well before using. Apply evenly on the prepared subfloor using a velour roller; work from out of the container without letting the adhesive pool.

Lay the flooring after an appropriate airing time and press it down firmly.

After laying, roll the complete area again with the articulated roller. The laid area can be directly walked upon and subjected to a load.

For conductive laying of suitable modular textile flooring, mix WAKOL D 3110 Modular Flooring Fixation with WAKOL DL 352 Conductive Dispersion in a ratio of 4,4 :1.

Important

Processing not below floor temperature of +15 °C and room temperature of +18 °C, as well as room humidity preferably between 40 % and 65 %, maximum 75 %. All information is based on approx. 20 °C and 50 % relative air humidity.

Differing room climate conditions lead to different times.

In cold weather, warm up all laying materials in a heated room before use.

We guarantee the uniform high quality of our products. All data is based on tests and many years of practical experience and refers to standardised conditions. The variety of materials used and the different construction site conditions, which lie beyond our control, preclude any claims based on this data. We therefore recommend making sufficient trials. Accompanying flooring manufacturer's instructions and the current national standards must be observed. We gladly provide technical advice.

F31TBEZ, R0, 10/11/2016

Wakol GmbH
Bottenbacher Straße 30
D-66954
Pirmasens
Tel. +49 6331 8001 131
Fax +49 6331 8001 890
www.wakol.com

Wakol GmbH
Industriestraße 5
A-6841
Mäder
Tel. +43 5523 64 700
Fax +43 5523 64 700 64
www.wakol.at

Wakol Adhesa AG/SA
Bionstraße 5
CH-9015
St. Gallen
Tel. +41 31 9210 755
Fax +41 31 9212 968
www.wakoladhesa.ch

Wakol Foreco srl
A Via Kennedy 75
I-20010
Marcallo con Casone
Tel. +39 02 9761 939
Fax +39 02 97 253 021
www.wakolforeco.it

Loba-Wakol Polska Sp.z o.o.
ul. Sławęcińska 16, Macierzysz
PL-05-850
Ożarów Mazowiecki
Tel. +48 22 436 24 20
Fax +48 22 436 24 21
www.loba-wakol.pl

Lecol Chemie B.V.
Schutweg 6
NL-5145 NP
Waalwijk
Tel. +31 416 566 540
Fax +31 416 566 531
www.lecol.nl

The product data sheets can be found in their latest version at www.wakol.com.

This Technical Information of 18.08.2026 supersedes all previous versions.

F31TBEZ, R0, 10/11/2016

Wakol GmbH
Bottenbacher Straße 30
D-66954
Pirmasens
Tel. +49 6331 8001 131
Fax +49 6331 8001 890
www.wakol.com

Wakol GmbH
Industriestraße 5
A-6841
Mäder
Tel. +43 5523 64 700
Fax +43 5523 64 700 64
www.wakol.at

Wakol Adhesa AG/SA
Bionstraße 5
CH-9015
St. Gallen
Tel. +41 31 9210 755
Fax +41 31 9212 968
www.wakoladhesa.ch

Wakol Foreco srl
A Via Kennedy 75
I-20010
Marcallo con Casone
Tel. +39 02 9761 939
Fax +39 02 97 253 021
www.wakolforeco.it

Loba-Wakol Polska Sp.z o.o.
ul. Sławęcińska 16, Macierzysz
PL-05-850
Ożarów Mazowiecki
Tel. +48 22 436 24 20
Fax +48 22 436 24 21
www.loba-wakol.pl

Lecol Chemie B.V.
Schutweg 6
NL-5145 NP
Waalwijk
Tel. +31 416 566 540
Fax +31 416 566 531
www.lecol.nl