WAKOL Z 625 Levelling Compound

Technical Information

Area of application

Self-levelling, low-tension, cement-based levelling compound for smoothing out unevenness in layers 1 - 20 mm thick, non-elongated, 10 - 30 mm, elongated, under

- Textile flooring
- Elastic flooring
- Parquet (minimum thickness of 2 mm)
- Cork flooring

indoors.

WAKOL Z 625 Levelling Compound can be processed in combination with WAKOL D 3060 Plastification Additive; for details, please refer to the technical information for the WAKOL D 3060 Plastification Additive.

Special Features



1)


2)


3)

4)

5)

6)

7)


8)

- chromate reduced according to REACH
- suitable for chair castors from a layer thickness of 1 mm
- suitable for direct use in conjunction with surface treatment
- can be applied with a rakel
- self-levelling
- can be pumped
- suitable for heavy loads from a layer thickness of 3 mm

1) Based on the criteria of GEV (Association for Emission-controlled Laying Materials), classified as EMICODE EC1 PLUS: very low in emissions
2) Emissions class according to French law
3) Cement-based products, low chromate
4) Meets the requirements of the European Community
5) Connected Systems guarantee in the system with approved LOBA varnishes and oils. See https:// www.loba.de/en/products/connected-systems/
6) Suitable for underfloor heating
7) Suitable for exposure to castor wheels
8) Suitable for installing sport flooring

Technical data

Raw material base:	Special cement/quartz mixture with special plastic additives
Strength of coating:	non-elongated processing up to 20 mm elongated processing 10 - 30 mm with additives up to max. 65 by weight % (aggregation: WAKOL S 25 Elongating Sand or quartz sand 0 - 3 mm)
Mixture:	approx. 6,0 - 6,25 l water + 25 kg WAKOL Z 625 Levelling Compound
Processing time:	approx. 20 minutes
Suitable for walking:	after approx. 2 hours
Waiting time before laying:	up to 5 mm layer thickness, after 6 hours up to 10 mm layer thickness, after 12 hours up to 20 mm layer thickness, after 24 hours up to 30 mm layer thickness (diluted), after 24 hours
Storage time:	12 months; store in a cool and dry location, tightly seal any opened bags and use as soon as possible
Classification acc. to EN 13813:	CT-C35-F7

Application and consumption[9)]

Trowel Rakel approx. 1,5 kg/m²/mm layer thickness

9) Consumption is dependent on surface structure and absorbability of subfloor.

Subfloors

The subfloor as well as the room climate conditions must meet the requirements of the applicable standards and data sheets. Subfloors must be permanently dry, solid, level, free from cracks, dirt and adhesion-inhibiting substances. Use a suitable mechanical procedure to remove separating layers.

Depending on their type and condition, subfloors must be primed with a suitable Wakol primer. Drying times and application instructions for the primers can be found in the technical information for the relevant primer.

F31TBEZ, R0, 10/11/2016

Wakol GmbH
Bottenbacher Straße 30
D-66954
Pirmasens
Tel. +49 6331 8001 131
Fax +49 6331 8001 890
www.wakol.com

Wakol GmbH
Industriestraße 5
A-6841
Mäder
Tel. +43 5523 64 700
Fax +43 5523 64 700 64
www.wakol.at

Wakol Adhesa AG/SA
Bionstraße 5
CH-9015
St. Gallen
Tel. +41 31 9210 755
Fax +41 31 9212 968
www.wakoladhesa.ch

Wakol Foreco srl
A Via Kennedy 75
I-20010
Marcallo con Casone
Tel. +39 02 9761 939
Fax +39 02 97 253 021
www.wakolforeco.it

Loba-Wakol Polska Sp.z o.o.
ul. Sławęcińska 16, Macierzysz
PL-05-850
Ożarów Mazowiecki
Tel. +48 22 436 24 20
Fax +48 22 436 24 21
www.loba-wakol.pl

Lecol Chemie B.V.
Schutweg 6
NL-5145 NP
Waalwijk
Tel. +31 416 566 540
Fax +31 416 566 531
www.lecol.nl

Usage

Stir WAKOL Z 625 Levelling Compound in a clean stirring vessel with approx. 6,0 - 6,25 l clear, cold tap water until free of lumps. The mixing device must not exceed 600 rpm. Leave the compound to stand for approx. max. 1 minutes before briefly mixing it again.
Apply stirred compound with dripper, smoothing trowel or knife uniformly to the subfloor in the desired layer thickness. Before applying the levelling compound, check whether a sufficiently sized edge strip is available.

Protect the levelling compound layer from direct sunlight and draughts while it sets.

Important

Processing not below floor temperature of +15 °C and room temperature of +18 °C, as well as room humidity preferably between 40 % and 65 %, maximum 75 %. All information is based on approx. 20 °C and 50 % relative air humidity. Warm up all laying materials in due time in heated room.

Observe 2 mm minimum layer thickness on non-absorbent subfloors.

For levelling work with layer thickness above 5 mm on moisture-sensitive subfloors such as calcium sulphate screed or gypsum fibreboards prime using a Wakol reaction resin. Please consult the corresponding data sheet.

The layer thickness permitted on mastic asphalt (IC10 and IC15) is max. 5 mm; WAKOL A 830 Levelling Compound or WAKOL Z 515 Thin Screed should be used for layers that are thicker than this.

For applying levelling compound on wooden subfloors that are rigidly bolted or glued to the subfloor, only use WAKOL Z 610 Levelling Compound, dust-reduced, WAKOL Z 615 Levelling Compound, dust-reduced, WAKOL Z 625 Levelling Compound, WAKOL Z 630 Levelling Compound or WAKOL A 830 Levelling Compound in combination with WAKOL AR 114 Reinforcement Fibre or WAKOL Z 515 Thin Screed.

Do not sand levelling compound before laying parquet in order to ensure the best possible adhesion.

If water is absorbed too quickly (due to high floor temperatures, drafts, or highly absorbent subfloors), there is a risk of cracking and surface irregularities. The freshly applied levelling compound must be protected from drying out too quickly and should preferably be covered with flooring within 10 days. If laying within this period is not possible, the surface must be covered with PE film (construction foil 0.2 mm) or PE-coated paper ("milk carton paper").

When used as a floor covering, a suitable surface treatment must be applied.
We recommend the use of Loba products that are marked with the Connected Systems for levelling compounds.
Please contact the Application Technology department beforehand for details about the processing of the levelling compound when used as a floor covering.

We guarantee the uniform high quality of our products. All data is based on tests and many years of practical experience and refers to standardised conditions. The variety of materials

F31TBEZ, R0, 10/11/2016

Wakol GmbH
Bottenbacher Straße 30
D-66954
Pirmasens
Tel. +49 6331 8001 131
Fax +49 6331 8001 890
www.wakol.com

Wakol GmbH
Industriestraße 5
A-6841
Mäder
Tel. +43 5523 64 700
Fax +43 5523 64 700 64
www.wakol.at

Wakol Adhesa AG/SA
Bionstraße 5
CH-9015
St. Gallen
Tel. +41 31 9210 755
Fax +41 31 9212 968
www.wakoladhesa.ch

Wakol Foreco srl
A Via Kennedy 75
I-20010
Marcallo con Casone
Tel. +39 02 9761 939
Fax +39 02 97 253 021
www.wakolforeco.it

Loba-Wakol Polska Sp.z o.o.
ul. Sławęcińska 16, Macierzysz
PL-05-850
Ożarów Mazowiecki
Tel. +48 22 436 24 20
Fax +48 22 436 24 21
www.loba-wakol.pl

Lecol Chemie B.V.
Schutweg 6
NL-5145 NP
Waalwijk
Tel. +31 416 566 540
Fax +31 416 566 531
www.lecol.nl

used and the different construction site conditions, which lie beyond our control, preclude any claims based on this data. We therefore recommend making sufficient trials. Accompanying flooring manufacturer's instructions and the current national standards must be observed. We gladly provide technical advice.

The product data sheets can be found in their latest version at www.wakol.com.

This Technical Information of 25.08.2026 supersedes all previous versions.

F31TBEZ, R0, 10/11/2016

Wakol GmbH
Bottenbacher Straße 30
D-66954
Pirmasens
Tel. +49 6331 8001 131
Fax +49 6331 8001 890
www.wakol.com

Wakol GmbH
Industriestraße 5
A-6841
Mäder
Tel. +43 5523 64 700
Fax +43 5523 64 700 64
www.wakol.at

Wakol Adhesa AG/SA
Bionstraße 5
CH-9015
St. Gallen
Tel. +41 31 9210 755
Fax +41 31 9212 968
www.wakoladhesa.ch

Wakol Foreco srl
A Via Kennedy 75
I-20010
Marcallo con Casone
Tel. +39 02 9761 939
Fax +39 02 97 253 021
www.wakolforeco.it

Loba-Wakol Polska Sp.z o.o.
ul. Sławęcińska 16, Macierzysz
PL-05-850
Ożarów Mazowiecki
Tel. +48 22 436 24 20
Fax +48 22 436 24 21
www.loba-wakol.pl

Lecol Chemie B.V.
Schutweg 6
NL-5145 NP
Waalwijk
Tel. +31 416 566 540
Fax +31 416 566 531
www.lecol.nl